


# BALLADYA

**AFD:** 22.8  $\mu$   
**SD:** 4.5  $\mu$   
**CV:** 19.9 %  
**CF:** 94.7 %  
**Curve:** 34.0 Dg/mm  
**Min:** 20.6  $\mu$   
**Max:** 24.4  $\mu$   
**Staple:** 80.0 mm

% of Fibers




*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# BALLADYA

**AFD:** 22.8  $\mu$   
**SD:** 4.5  $\mu$   
**CV:** 19.9 %  
**CF:** 94.7 %  
**Curve:** 34.0 Dg/mm  
**Min:** 20.6  $\mu$   
**Max:** 24.4  $\mu$   
**Staple:** 80.0 mm



*Alpaca Fiber Testing USA*