


CALLINA

AFD: 22.7 μ
SD: 5.5 μ
CV: 24.4 %
CF: 89.8 %
Curve: 39.0 Dg/mm
Min: 21.0 μ
Max: 27.4 μ
Staple: 90.0 mm

% of Fibers

Alpaca Fiber Testing USA



CALLINA

AFD: 22.7 μ
SD: 5.5 μ
CV: 24.4 %
CF: 89.8 %
Curve: 39.0 Dg/mm
Min: 21.0 μ
Max: 27.4 μ
Staple: 90.0 mm

